



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09G 1/02, 1/04, B24B 1/00, H05K 3/26	A1	(11) International Publication Number: WO 99/64527 (43) International Publication Date: 16 December 1999 (16.12.99)
(21) International Application Number: PCT/US99/13244 (22) International Filing Date: 10 June 1999 (10.06.99) (30) Priority Data: 60/088,849 10 June 1998 (10.06.98) US (71) Applicant: RODEL HOLDINGS, INC. [US/US]; Suite 1300, 1105 North Market Street, Wilmington, DE 19899 (US). (72) Inventors: SACHAN, Vikas; 121 Brook Run, Hockessin, DE 19707 (US). KEGERISE, Elizabeth; 413 Christina Mill Road, Newark, DE 19711 (US). YE, Christine; Apartment 806, 758 Christiana Road, Newark, DE 19713 (US). PIERCE, Keith, G.; 54-B Benny Street, Newark, DE 19713 (US). LACK, Craig, D.; 438 Greenwood Drive, Wilmington, DE 19808 (US). THOMAS, Terence, M.; 8029 Grovewood Drive, Mentor, OH 44060 (US). BURKE, Peter, A.; 104 Interlachen Court, Avondale, PA 19311 (US). GETTMAN, David; 3909 Christiana Meadows, Bear, DE 19701 (US). LANE, Sarah; 162 Russell Road, Elkton, MD 21921 (US). (74) Agent: BENSON, Kenneth, A.; Suite 1300, 1105 North Market Street, Wilmington, DE 19899 (US).		(81) Designated States: CN, JP, KR, SG, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: COMPOSITION AND METHOD FOR POLISHING IN METAL CMP

(57) Abstract

A composition is provided in the present invention for polishing a composite semiconductor structure containing a metal layer (such as tungsten, aluminum, or copper), a barrier layer (such as tantalum, tantalum nitride, titanium, or titanium nitride), and an insulating layer (such as SiO₂). The composition comprises an aqueous medium, an abrasive, an oxidant, an organic polymer that attenuates removal of the oxide film having a degree of polymerization of at least 5 and having a plurality of moieties having affinity to surface groups contained on silicon dioxide surfaces. The composition may optionally comprise a complexing agent and/or a dispersant.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

5 **COMPOSITION AND METHOD FOR POLISHING IN
METAL CMP**

 The present application claims priority to co-pending
provisional application No. 60/088,849 filed June 10, 1998.

10

BACKGROUND OF THE INVENTION

Field of the Invention

15 The invention described in this patent pertains to the polishing
and planarization of integrated circuit surfaces, particularly those
comprising a metal, a barrier layer, and an insulating layer.

Discussion of Related Art

20

 Chemical/Mechanical Planarization (or polishing), or CMP, is
an enabling technology used in the semiconductor industry to
remove/planarize various thin films from the surface of
semiconductor substrates during the production of integrated circuits.
25 While initial applications of this technology focused on the polishing
of dielectric films (such as SiO₂), polishing of metal films used for
circuit interconnects is undergoing rapid growth. Currently, tungsten
and aluminum are the most common metals used for interconnect
structures. However, copper interconnects, coupled with low-k
30 dielectrics, have the potential (when compared to Al/SiO₂) to
increase chip speed, reduce the number of metal layers required,
minimize power dissipation, and reduce manufacturing costs.

 However, the challenges associated with the successful
35 integration of copper interconnects are not trivial. A typical copper
interconnect structure contains a trench formed in silicon dioxide
(typically 10,000 angstroms deep and 1-100 microns wide) formed
above the silicon substrate. A barrier layer of material (used to
improve adhesion of the copper as well as inhibit the diffusion of
40 copper into the dielectric structure) is typically deposited after the

trench is formed, and is ususally composed of either tantalum, tantalum nitride, titanium, or titanium nitride. This barrier material is also deposited on the horizontal dielectric surface above the trench. The barrier layer is typically < 1000 angstroms thick. Copper is then
5 deposited by chemical vapor deposition or electroplating on top of this structure in order to fill the trench structure. To insure complete filling of the trench, an overlayer of copper of 10,000-15,000 angstroms is usually required. CMP is then used to remove the overburden of copper above the trench and the horizontal barrier
10 material above the trench. In order to do this successfully and economically, the copper removal should be as fast as possible, typically above 3000 angstroms/minute. Also, to avoid removal of the copper within the trench (typically referred to as "dishing"), removal of the barrier layer at rates comparable to that of the copper
15 film are necessary. Additionally, to avoid degradation of the SiO₂ film beneath the barrier layer (typically referred to as "erosion"), and to improve global planarization, the removal rate of the underlying dielectric film should be as low as possible. In summary, the selectivity for the removal rate of the barrier film (tantalum, tantalum
20 nitride, titanium, or titanium nitride) should be high with respect to the copper film, while the selectivity for the removal rate of the dielectric film (SiO₂) should be low (preferably <100:1).

To accomplish these requirements, a two-step polishing
25 process using two different slurries has been proposed. In U.S. Pat. No. 5,676,587, Selective Polish Process for Titanium, Titanium Nitride, Tantalum, and Tantalum Nitride, a two-step process using first (1) a slurry to remove the majority of the metal film (such as tungsten or copper) and second (2) a slurry to remove the barrier film
30 is proposed.

To suppress the removal rate of silicon dioxide during CMP processes, various additives have been previously suggested that passivate the silicon dioxide surface. In U.S. Pat. No. 5,614,444,
35 Method of using Additives with Silica-Based slurries to Enhance Selectivity in Metal CMP, an additive comprising at least one polar component and one apolar component is suggested to suppress oxide removal. This patent lists a number of compounds containing both polar and non-polar groups, which are either anionic (potassium
40 butylsulphate), cationic (tetrabutyl ammonium hydroxide), or non-

ionic (butanol). However, this patent claims as a necessity both a polar and apolar component (group) to be present.

5 In U.S. Pat. No. 5,876,490 polyelectrolytes are used to coat the abrasive particles in a slurry. The polyelectrolytes impart normal stress effects to the slurries. In solution, the polyelectrolytes exhibit normal stress effects and their adsorption on the abrasive particles impart the same behavior to the particles.

10 According to U.S. Pat. No. 5,876,490, in order to achieve planarization, the quantity of polyelectrolyte in the abrasive suspension is such that a fraction of the particles will be coated with the polyelectrolyte, while another fraction of the abrasive particles will remain uncoated. In order to achieve this, the weight percent of
15 the polyelectrolyte should be about 5 to about 50 percent, preferably about 15 to about 30 percent by weight, and most preferably about 20 percent by weight of the abrasive particles in the slurry. These ratios depend somewhat on the relative size of the abrasive particles and the polyelectrolyte.

20 The slurry compositions of U.S. Pat. No. 5,876,490 that contain the polyelectrolyte are preferably prepared by adding the polyelectrolyte to the slurry already containing the abrasive particles, thereby coating a fraction of the abrasive particles "in situ." In an
25 alternative procedure, a fraction of the abrasive particles can be precoated and then admixed with the slurry containing the remaining abrasive particles which will be uncoated. In addition, it may be desirable to pretreat a portion of the abrasive particles to render them more susceptible to adsorption of the polyelectrolyte from the slurry.

30 U.S. Patents Nos. 5,391,258; 5,476,606; 5,738,800; 5,770,103 describe compounds which in CMP slurries provide attenuation of silicon dioxide removal. These patents are hereby incorporated by reference and made a part of this specification.

35

SUMMARY OF THE INVENTION

40 The present invention is directed to one or more organic polymers which have surprisingly been found to attenuate the

removal of the oxide film during metal CMP and offers an improvement over earlier slurries. This organic polymer is a high molecular weight organic polymer containing a carbon backbone with functional moieties extending from the backbone. The functional moieties interact strongly with the silicon dioxide surface so as to provide a protective layer that inhibits the removal of the silicon dioxide film at appreciable levels. The mechanism of interaction between the functional moieties and the hydroxyl surface is, though not limited to, that observed in the hydrogen bonding of polar species (such as the interaction of hydroxyl groups). The organic polymer is further defined as a high molecular weight organic material, having a degree of polymerization of at least 3 (i.e., 3 monomeric units polymerized into a molecule), more preferably more than 10, and most preferably greater than 50. The organic polymer comprises a plurality of moieties having affinity to surface groups (i.e., silanol and siloxane) contained on silicon dioxide surfaces. These moieties are commonly polar moieties, such as, but not limited to, hydroxy, carboxy, carbonyl, alkoxy, sulphonyl, and phosphonyl. Examples of this type of organic polymer molecule includes poly-vinyl alcohol, poly-vinylpyrrolidone, poly-methyl methacrylate, poly-formaldehyde, poly-ethylene oxide, poly-ethylene glycol, and poly-methacrylic acid.

Many of these same compounds are mentioned as being useful for coating abrasive particles in U.S. Patent No. 5,876,490 as discussed above. Their use as a silicon dioxide rate suppressant is not mentioned in '490. Moreover, the polyelectrolytes of the present invention have been found to be effective as a silicon dioxide rate suppressant at concentrations below about 5 percent by weight of the abrasive particles in a slurry. They have also been found to be effective when having a molecular weight of greater than about 10,000.

Another aspect of the present invention is a method of polishing a substrate comprising a metal and an insulator wherein the substrate is pressed against a polishing pad, the substrate and the pad are moved relative to each other, and a polishing composition is applied to said pad during the polishing operation. The polishing compositions of the present invention are useful for such methods.

DESCRIPTION OF PREFERRED EMBODIMENTS

The slurries used in this invention were prepared with the following general protocol. In every case, the chemical additives are first dissolved in deionized water. After all the chemical additives are dissolved in the deionized water, the pH is adjusted to the desired level. In a separate vessel, the abrasive package which is comprised of the inorganic oxide abrasive particles in deionized water is mixed. The pH of the abrasive package is also adjusted to the desired level. The final step in the slurry formulation preparation is the combining of the aqueous chemical package with the aqueous abrasive package. Contrary to prior art, a polyelectrolyte additive can be added into this aqueous solution without any special abrasive adsorption requirements.

Typically, the list of chemical additives includes an oxidizing agent, the organic polymer removal rate suppressant of this invention, and optionally a complexing agent and/or a dispersant. The order of mixing of this chemical package need only be chosen such that there is complete solubilization of all the additives.

A complex as defined in "Advanced Inorganic Chemistry", F. A. Cotton and G. Wilkinson, 3rd ed., Wiley Interscience is: "The terms 'coordination compound' and 'complex' may be broadly defined to embrace all species, charged or uncharged, in which a central atom is surrounded by a set of outer or ligand atoms, whereby the energy of the system is lowered. (ie $E > 0$ and/or $G < 0$). An example of a neutral complex is SF_6 , where the central S atom is surrounded by 6 F atoms in an octahedral arrangement. An example of a positive complex ion is $[\text{Cu}(\text{NH}_3)_4]^{2+}$, where the central Cu atom is surrounded by 4 NH_3 molecules in a tetrahedral arrangement. An example of a negative complex ion is $[\text{Cu}(\text{Cl})_5]^{3-}$, where the central Cu atom is surrounded by 5 Cl atoms in a pentagonal bipyramid arrangement." Examples of common ligands, which in the slurries of this invention are called complexing agents, are acetic acid, citric acid, ethyl acetoacetate, glycolic acid, glyoxylic acid, lactic acid, malic acid, oxalic acid, salicylic acid, sodium diethyldithiocarbamate, succinic acid, tartaric acid, thioglycolic acid, glycine, alanine, aspartic acid, ethylene diamine, trimethylene diamine, 1,2-ethanedithiol, 1,4 dithiothreitol, bis(methylthio)methane,

dimethyldithiocarbamate, 5-methyl 3,4 thiadiazole-2-thiol, malonic acid, gluteric acid, 3-hydroxybutyric acid, propionic acid, phthalic acid, isophthalic acid, 3-hydroxy salicylic acid, 3,5-dihydroxy salicylic acid, and galic acid.

5

The slurries of this invention may optionally comprise a dispersant. Aque

The oxidizing agent in the compositions of the present invention may be comprised of any of the common oxidizing agents such as nitrates, iodates, chlorates, perchlorates, chlorites, sulphates, persulphates, peroxides, ozonated water, and oxygenated water. Oxidizing agents can be used in slurries for CMP at concentrations of about 0.01% to about 7% by weight. Generally they are used at concentrations of about 1% to about 7% by weight. An iodate is a preferred oxidizing agent. Most preferred is potassium iodate at about 2% to about 4% by weight.

15

In the examples presented below, silica and titania were predominantly used as the abrasive component in the slurries tested. However, any metal oxide or polishing abrasive (such as alumina, ceria, zirconia, barium carbonate, or diamond) could also be used.

20

EXAMPLES

25

Unless otherwise indicated, all percentages mentioned in the following examples are by weight in the slurries described.

Example 1: Table 1 shows the results of polishing copper, tantalum, and silicon dioxide (formed from TEOS) wafers containing various amounts of complexing agents and oxidants. These experiments were carried out on an IPEC/Westech 372U polisher using a Rodel IC1400 pad under the conditions of 5 psi down pressure, 60 rpm carrier speed, 50 rpm platen speed, and a slurry flowrate of 110 ml/min. 6 inch sheet wafers were used. All slurries in this example contain 10% colloidal silica abrasive (Klebosol 1498), were at a pH of 10.5, and were adjusted to that pH with varying amounts of potassium hydroxide.

30

35

Table 1

40

Sample	% Oxalic Acid	% Hydrogen Peroxide	RR Cu	RR Ta	RR SiO ₂
1	0	0	202	340	1149
2	0	2	314	495	1261
3	3	0	214	416	1264
4	3	2	2038	1035	1202

These results show that in order to get high removal rates of both copper and the tantalum, it is necessary to have both a complexing agent that increases the solubility of both metals in aqueous solution, as well as contain a oxidant such as hydrogen peroxide. With this combination of components, it is possible to have satisfactory removal rates of copper while retaining a good selectivity (approximately 2:1) between the removal rates of copper and tantalum. It is also apparent from this example that additional components are needed to inhibit the removal rate of silicon dioxide.

Example 2: Table 2 shows the results of polishing copper and silicon dioxide (formed from TEOS) wafers containing various amounts of agents that are thought to suppress oxide removal. These experiments were carried out on an IPEC/Westech 372U polisher using a Rodel IC1400 pad under the conditions of 5 psi down pressure, 3 psi back pressure, 60 rpm carrier speed, 50 rpm platen speed, and a slurry flowrate of 110 ml/min. 6 inch sheet wafers were used. All slurries in this example contain 10% colloidal silica abrasive (Klebosol 1498), 3% oxalic acid, 0.2% ammonium hydroxide, 0.2% hydrogen peroxide, and were adjusted to the pH listed with varying amounts of potassium hydroxide. The poly-vinylpyrrolidone (PVP) used in the experiment below has a molecular weight between 10,000 and 30,000 daltons (i.e. has a degree of polymerization between 90 and 270). Sodium dodecyl sulfate (SDS), a traditional surfactant with a polar functional group and a long-chain hydrocarbon tail, is also tested for comparison.

Table 2

Sample	% PVP	% SDS	pH	RR Cu	RR	Cu:SiO ₂
--------	-------	-------	----	-------	----	---------------------

					SiO ₂	Selectivity
1	0	0	6	8566	1070	8
2	0	0	8	8166	1066	7.7
3	1	0	6	6727	133	50
4	1	0	8	7207	129	56
5	0	0.5	6	8591	1093	7.9
6	0	0.5	8	8187	1076	7.6

These results show that in order to get high removal rates of copper and low removal rates of silicon dioxide (i.e., high selectivities), it is necessary to have an additional component such as PVP to suppress the silicon dioxide removal rate while not suppressing the copper removal rate. Also, traditional surfactants like SDS are observed not to significantly effect the removal rate of oxide or copper films.

10

Example 3: Table 3 shows the results of polishing copper and tantalum wafers containing various amounts of complexing agents and oxidants. These experiments were carried out on an IPEC/Westech 372U polisher using a Rodel IC1400 pad under the conditions of 5 psi down pressure, 3 psi back pressure, 60 rpm carrier speed, 50 rpm platen speed, and a slurry flowrate of 110 ml/min. 6 inch sheet wafers were used. All slurries in this example contain 10% colloidal silica abrasive (Klebosol 1498), 0.75% of PVP, and were adjusted to that pH with varying amounts of nitric acid or potassium hydroxide.

25

Table 3

Sample	% Oxalic Acid	% Hydrogen Peroxide	pH	RR Cu	RR Ta
--------	---------------	---------------------	----	-------	-------

1	0	0	2.5	206	920
2	0	0	6	226	132
3	0	2	2.5	866	372
4	0	2	6	256	312
5	2	0	2.5	115	442
6	2	0	6	75	249
7	2	2	2.5	6237	430
8	2	2	6	1490	489

These results show that in order to get high removal rates of copper while retaining good tantalum removal rates, it is necessary to have both an oxidant and a complexing agent contained in the slurry.

Example 4: Table 4 shows the results of polishing copper, tantalum, tantalum nitride, and titanium wafers at two different pH levels. These experiments were carried out on an IPEC/Westech 372U polisher using a Rodel IC1400 pad under the conditions of 5 psi down pressure, 3 psi back pressure, 50 rpm carrier speed, 60 rpm platen speed, and a slurry flowrate of 120 ml/min. 6 inch sheet wafers were used. All slurries in this example contain 7% titania abrasive (Degussa P-25), 0.7% of PVP, 4% oxalic acid, 1% hydrogen peroxide, and were adjusted to the specified pH by varying the amount of potassium hydroxide.

Table 4

Sample	pH	RR Cu	Cu:Ta Selectivity	Cu: TaN Selectivity	Cu:Ti Selectivity	Cu:SiO ₂ Selectivity
1	5.0	2950	7	3	-	> 100
2	6.2	1600	3.9	1.3	2.6	> 100

These results show that, by using an oxide suppressant, such as PVP, very high Cu:SiO₂ selectivities (above 100:1) can be achieved.

Example 5: Table 5 shows the results of polishing patterned wafers. These experiments were carried out on an IPEC/Westech 372U polisher. For Sample 1, a Rodel IC1400/K-XY pad was used

with the polishing conditions of 3 psi down pressure, 2 psi back pressure, 40 rpm carrier speed, 65 rpm platen speed, and a slurry flowrate of 150 ml/min. For Sample 2, a Rodel IC1000 pad under the conditions of 4 psi down pressure, 3 psi back pressure, 75 rpm carrier speed, 60 rpm platen speed, and a slurry flowrate of 150 ml/min. All slurries in this example contain 7% titania abrasive (Degussa P-25), 0.7% of PVP, 4% oxalic acid, 1% hydrogen peroxide, and were adjusted to the specified pH by varying the amount of potassium hydroxide.

10

Table 5

Sample	pH	Dishing 1 micron line	Dishing 100 micron pad	Oxide Erosion 50% pattern density
1	5.0	1836	1390	49
2	6.2	1120	-	560

These results show that the oxide erosion experienced with slurries containing compounds such as PVP is much lower than that typically observed.

Example 6: The use of a polymeric additive has been shown to be effective at a wide range of dosing levels. In this example, PVP was added to a copper polishing slurry at a level of about 4% based on the total abrasive using the slurry preparation method described above. Polishing performance was measured using a Strasbaugh 6EC with a down force of 5 psi and a platten speed of 80 rpm. Slurry flow rate was 150 ml/min.

In this example, the test slurry comprised KIO₃ as an oxidant and lactic acid as a copper complexing agent, and 4% PVP based on the abrasive present. The polishing removal rate results are given in Table 6 below.

Table 6

Removal Rate Performance of a PVP containing Copper Slurry

35

Copper RR (A.min)	TaN RR (A/min)	Oxide RR (A/min)
4465	137	165

Based on the data in Table 7, it is clear that PVP can be utilized at low concentrations in a metal polishing slurry in order to achieve good selectivity and low oxide removal rates.

5

Nothing in the foregoing Examples and discussion should in any way limit the scope of the present invention which is given in the claims to follow.

CLAIMS

1. A composition, which is an aqueous slurry useful for the chemical-mechanical polishing of substrates which contain a metal and an insulator, comprising: water, submicron abrasive particles, an oxidant, and an organic polymer which attenuates removal of an oxide film said organic polymer having a degree of polymerization of at least 3 and having a plurality of moieties having affinity to surface groups contained on silicon dioxide surfaces.
2. A composition according to Claim 1 wherein said moieties are from the group consisting of hydroxy, carboxy, carbonyl, alkoxy, sulphonyl, and phosphonyl.
3. A composition according to Claim 2 wherein said organic compound is from the group consisting of poly-vinyl alcohol, poly-vinylpyrrolidone, poly-methyl methacrylate, poly-formaldehyde, poly-ethylene oxide, poly-ethylene glycol, and poly-methacrylic acid.
4. A composition according to Claim 3 wherein said organic compound is poly-vinylpyrrolidone.
5. A composition according to Claim 1 wherein said organic compound is present in said composition at a concentration less than 5 weight percent based on the weight of said submicron abrasive particles present in said composition.
6. A composition according to Claim 1 wherein said organic compound has a molecular weight of greater than 10,000.
7. A composition according to Claim 1 wherein said composition also comprises a complexing agent.
8. A composition according to Claim 1 wherein said composition also comprises a dispersant.
9. A method of polishing a substrate comprising a metal and an insulator wherein said substrate is pressed against a polishing pad, said substrate and said pad are moved relative to each other, and a polishing composition is applied to said pad during the polishing

operation, said polishing composition comprising: water. submicron abrasive particles, an oxidant, and an organic polymer which attenuates removal of an oxide film said organic polymer having a degree of polymerization of at least 3 and having a plurality of
5 moieties having affinity to surface groups contained on silicon dioxide surfaces.

10. A method according to Claim 9 wherein said moieties are from the group consisting of hydroxy, carboxy, carbonyl, alkoxy,
10 sulphonyl, and phosphonyl.

11. A method according to Claim 10 wherein said organic compound is from the group consisting of poly-vinyl alcohol, poly-vinylpyrrolidone, poly-methyl methacrylate, poly-formaldehyde,
15 poly-ethylene oxide, poly-ethylene glycol, and poly-methacrylic acid.

12. A composition according to Claim 11 wherein said organic compound is poly-vinylpyrrolidone.

20 13. A composition according to Claim 9 wherein said organic compound is present in said composition at a concentration less than 5 weight percent based on the weight of said submicron abrasive particles present in said composition.

25 14. A composition according to Claim 9 wherein said organic compound has a molecular weight of greater than 10,000.

15. A composition according to Claim 9 wherein said composition also comprises a complexing agent.

30

16. A composition according to Claim 9 wherein said composition also comprises a dispersant.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US99/13244

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : C09G 1/02, 1/04; B24B 1/00; H05K 3/26

US CL : 51/307, 308, 309; 252/79.1; 216/89; 438/693, 692

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 51/307, 308, 309; 252/79.1; 216/89; 438/693, 692

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X,P	US 5,876,490 A (RONAY) 02 March 1999 (02-03-99), col. 3, line 9-col. 12, line 18.	1-3,8-11,16
X	US 5,352,277 A (SASAKI) 04 October 1994 (04-10-94), col. 21, line 3-col. 26, line 37.	1-6,9-14

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
B earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*A* document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

03 AUGUST 1999

Date of mailing of the international search report

31 AUG 1999

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCTAuthorized officer
